



Technical Datasheet

| | |
|---------------------|---|
| PRODUCT CODE | CM AP 170 |
| PRODUCT DESCRIPTION | ARAMID FABRIC - 1210 Dtex 170 gr/m2 Plain |

| | |
|--------------|-------------------------------------|
| LAYER | REINFORCEMENT CONSTRUCTION |
| WARP PER END | 7.0 / Warp - 1210 Dtex ARAMID FIBER |
| WEFT PER END | 7.0 / Weft - 1210 Dtex ARAMID FIBER |

FIBER PROPERTIES



| | |
|---------------------|--|
| YARN | 1210 Dtex Type 2200 High Modulus Yarn / TWARON - TEIJIN ARAMID |
| TENSILE STRENGTH | ARAMID: 3157 MPa |
| TENSILE MODULUS | ARAMID: 110 GPa |
| STRAIN | ARAMID: 2.8% |
| RESIN COMPATIBILITY | POLYESTER,VINYLESTER,EPOXY RESINS |
| TEST METHOD | ISO 10618 |

ROLL INFO

| | |
|-------------|--------|
| ROLL WEIGHT | 17 KG |
| ROLL LENGTH | 100 MT |
| ROLL WIDTH | 100 CM |

| | |
|-----------|---|
| PACKAGING | ALL ROLLS ARE WRAPPED WITH PE SHEET AND IN SINGLE CARDBOARD BOXES |
|-----------|---|

| | |
|---------|---|
| STORAGE | STORE IN A COOL AND DRY PLACES KEEP AWAY FROM DIRECT SUN LIGHT. |
|---------|---|

| | |
|--|--|
| CERTIFICATION   | CARBOMID FABRICS ARE PRODUCED BY BIRLIK TICARET AS WHO IS RUN BY ISO 9001:2008 QA SYSTEM |
|--|--|