



Technical Datasheet

PRODUCT CODE	CM AP 709 Ballistic Aramid
PRODUCT DESCRIPTION	ARAMID FABRIC - 930 Dtex 200 gr/m2 Plain

LAYER	REINFORCEMENT CONSTRUCTION
WARP PER END	10.5 / Warp - 930 Dtex ARAMID FIBER
WEFT PER END	10.5 / Weft - 930 Dtex ARAMID FIBER

FIBER PROPERTIES



YARN	ARAMID 930 Dtex 1000F Type 2040 Ballistic Fiber
TENSILE STRENGTH	ARAMID: 225 cN/tex
TENSILE MODULUS	ARAMID: 89 GPA
STRAIN	ARAMID: 3.45%
RESIN COMPATIBILITY	POLYESTER,VINYLESTER,EPOXY RESINS
TEST METHOD	ISO 10618

ROLL INFO

ROLL WEIGHT	26 KG
ROLL LENGTH	100 MT
ROLL WIDTH	130 CM

PACKAGING	ALL ROLLS ARE WRAPPED WITH PE SHEET AND IN SINGLE CARDBOARD BOXES
-----------	---

STORAGE	STORE IN A COOL AND DRY PLACES KEEP AWAY FROM DIRECT SUN LIGHT.
---------	---

CERTIFICATION  	CARBOMID FABRICS ARE PRODUCED BY BIRLIK TICARET AS WHO IS RUN BY ISO 9001:2008 QA SYSTEM
---	--